

## SECTION 11

### AGGREGATE SUBBASE

#### 11-1 GENERAL

- A. This work shall consist of furnishing, spreading and compacting aggregate subbase in conformance with Section 25, "Aggregate Subbases", of the Caltrans Standard Specifications and in conformance with the lines, grades and dimensions shown on the Drawings and typical cross-sections except as modified herein.
- B. The relative compaction of each layer of compacted subbase material shall be not less than 95 percent.
- C. The surface of the finished subbase shall not vary more than 0.05 foot above or below the grade established by the Engineer.

END OF SECTION

## SECTION 12

### AGGREGATE BASE

#### 12-1 GENERAL

- A. This work shall consist of furnishing, spreading and compacting Class 2 aggregate base as detailed in Section 26, "Aggregate Bases", of the Caltrans Standard Specifications and in conformance with the lines, grades and dimensions shown on the Drawings and typical cross-sections, except as modified herein.
- B. The relative compaction of each layer of compacted base material shall be not less than 95 percent.
- C. The surface of the finished base shall not vary more than 0.05 foot above or below the grade established by the Engineer.

END OF SECTION